

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
5.500	15.50	J-55	4040	4810	4810	4810	4810	202	217	300	248	0.275	4.950	4.825	
5.500	15.50	K-55	4040	4810	4800	4810	4810	222	239	366	248	0.275	4.950	4.825	
5.500	17.00	J-55	4910	5320	5320	5320	5320	229	247	329	273	0.304	4.892	4.767	
5.500	17.00	K-55	4910	5320	5320	5320	5320	252	272	402	273	0.304	4.892	4.767	
5.500	17.00	L-80	6390	7740		7740	7740		338	428	397	0.304	4.892	4.767	
5.500	17.00	HCL-80	8580	7740		7740	7740		356	462	397	0.304	4.892	4.767	
5.500	17.00	N-80	6390	7740		7740	7740		348	446	397	0.304	4.892	4.767	
5.500	17.00	HCN-80	8580	7740		7740	7740		356	462	397	0.304	4.892	4.767	
5.500	17.00	C-90	6740	8710		8710	8710		356	456	447	0.304	4.892	4.767	
5.500	17.00	S-95	8580	9190		9190	9190		392	498	471	0.304	4.892	4.767	
5.500	17.00	T-95	6940	9190		9190	9190		374	480	471	0.304	4.892	4.767	
5.500	17.00	C-95	6940	9190		9190	9190		374	480	471	0.304	4.892	4.767	
5.500	17.00	HCP-110	8580	10640		10640	10640		445	568	546	0.304	4.892	4.767	
5.500	17.00	P-110	7480	10640		10640	10640		445	568	546	0.304	4.892	4.767	
5.500	17.00	HCQ-125	8580	12090		12090	12090		481	620	620	0.304	4.892	4.767	
5.500	17.00	Q-125	7890	12090		12090	12090		481	620	620	0.304	4.892	4.767	
5.500	20.00	L-80	8830	9190		9190	8990		416	503	466	0.361	4.778	4.653	
5.500	20.00	HCL-80	10630	9190		9190	8990		438	542	466	0.361	4.778	4.653	
5.500	20.00	N-80	8830	9190		9190	8990		428	524	466	0.361	4.778	4.653	
5.500	20.00	HCN-80	10630	9190		9190	8990		438	542	466	0.361	4.778	4.653	
5.500	20.00	C-90	9630	10340		10340	10120		438	436	525	0.361	4.778	4.653	
5.500	20.00	S-95	10630	10910		10910	10680		482	585	554	0.361	4.778	4.653	
5.500	20.00	T-95	10010	10910		10910	10680		460	563	554	0.361	4.778	4.653	
5.500	20.00	C-95	10010	10910		10910	10680		460	563	554	0.361	4.778	4.653	
5.500	20.00	P-110	11100	12630		12630	12360		548	667	641	0.361	4.778	4.653	
5.500	20.00	Q-125	12080	14360		14360	14050		592	728	729	0.361	4.778	4.653	
5.500	20.00	V-150	13460	17230		17230	16860		701	865	874	0.361	4.778	4.653	
5.500	23.00	L-80	11160	10560		9880	8990		489	550	530	0.415	4.670	4.545	
5.500	23.00	HCL-80	12450	10560		9880	890		514	551	530	0.415	4.670	4.545	
5.500	23.00	N-80	11160	10560		9880	8990		502	579	530	0.415	4.670	4.545	
5.500	23.00	HCN-80	12450	10560		9880	8990		514	579	530	0.415	4.670	4.545	
5.500	23.00	C-90	12380	11880		11110	10120		514	579	597	0.415	4.670	4.545	
5.500	23.00	S-95	12940	12540		11730	10680		566	637	630	0.415	4.670	4.545	
5.500	23.00	T-95	12940	12540		11730	10680		540	608	630	0.415	4.670	4.545	
5.500	23.00	C-95	12940	12540		11730	10680		540	608	630	0.415	4.670	4.545	
5.500	23.00	P-110	14540	14530		13580	12360		643	724	729	0.415	4.670	4.545	
5.500	23.00	Q-125	16070	16510		15430	14050		694	782	829	0.415	4.670	4.545	
5.500	23.00	V-150	18390	19810		18520	16860		823	927	995	0.415	4.670	4.545	
5.500	26.00	C-90	14240	13630		11110	10120		598	579	676	0.476	4.548	4.423	
5.500	26.00	T-95	15030	14390		11730	10680		628	608	714	0.476	4.548	4.423	
5.500	26.00	C-95	15030	14390		11730	10680		628	608	714	0.476	4.548	4.423	
5.500	26.00	P-110	17400	16660		13580	12360		748	724	826	0.476	4.548	4.423	
5.500	26.00	Q-125	19770	18930		15430	14050		808	782	939	0.476	4.548	4.423	

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
5.500	26.00	V-150	23720	22720		18520	16860		957	927	1127	0.476	4.548	4.423	
5.500	26.80	C-90	14880	14320							707	0.500	4.500	4.375	
5.500	26.80	T-95	15700	15110							746	0.500	4.500	4.375	
5.500	29.70	C-90	16510	16090							785	0.562	4.376	4.251	
5.500	29.70	T-95	17430	16990							828	0.562	4.376	4.251	
5.500	32.60	C-90	18130	17900							861	0.625	4.250	4.125	
5.500	32.60	T-95	19140	18810							909	0.625	4.250	4.125	
5.500	35.30	C-90	19680	19670							935	0.687	4.126	4.001	
5.500	35.30	T-95	20760	20770							987	0.687	4.126	4.001	
5.500	38.00	C-90	21200	21480							1007	0.750	4.000	3.875	
5.500	38.00	T-95	22380	22670							1063	0.750	4.000	3.875	
5.500	40.50	C-90	22650	23250							1076	0.812	3.876	3.751	
5.500	40.50	T-95	23920	24540							1136	0.812	3.876	3.751	
5.500	43.10	C-90	24080	25060							1144	0.875	3.750	3.625	
5.500	43.10	T-95	25400	26450							1208	0.875	3.750	3.625	