

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
7.625	24.00	H-40	2030	2750	2750			212			276	0.300	7.025	6.900	
7.625	26.40	J-55	2890	4140	4140	4140	4140	315	346	483	414	0.328	6.969	6.844	
7.625	26.40	K-55	2890	4140	4140	4140	4140	342	377	581	414	0.328	6.969	6.844	
7.625	26.40	L-80	3400	6020		6020	6020		482	635	602	0.328	6.969	6.844	
7.625	26.40	HCL-80	4850	6020		6020	6020		533	691	602	0.328	6.969	6.844	
7.625	26.40	N-80	3400	6020		6020	6020		490	659	602	0.328	6.969	6.844	
7.625	26.40	HCN-80	4850	6020		6020	6020		553	691	602	0.328	6.969	6.844	
7.625	26.40	C-90	3610	6780		6780	6780		532	681	677	0.328	6.969	6.844	
7.625	26.40	H2S-90	4850	6780		6780	6780		553	691	677	0.328	6.969	6.844	
7.625	26.40	S-95	4850	7150		7150	7150		568	740	714	0.328	6.969	6.844	
7.625	26.40	T-95	3710	7150		7150	7050		560	716	714	0.328	6.969	6.844	
7.625	26.40	H2S-95	4850	7150		7150	7050		560	716	714	0.328	6.969	6.844	
7.625	26.40	C-95	3710	7150		7150	7150		560	716	714	0.328	6.969	6.844	
7.625	26.40	HCP-110	4850	8280		8280	8280		654	845	827	0.328	6.969	6.844	
7.625	26.40	P-110	3920	8280		8280	8280		654	845	827	0.328	6.969	6.844	
7.625	29.70	L-80	4790	6890		6890	6890		566	721	683	0.375	6.875	6.750	
7.625	29.70	HCL-80	7150	6890		6890	6890		650	785	683	0.375	6.875	6.750	
7.625	29.70	N-80	4790	6890		6890	6890		575	749	683	0.375	6.875	6.750	
7.625	29.70	HCN-80	7150	6890		6890	6890		650	785	683	0.375	6.875	6.750	
7.625	29.70	C-90	5040	7750		7750	7750		625	773	769	0.375	6.875	6.750	
7.625	29.70	H2S-90	7150	7750		7750	7750		650	785	769	0.375	6.875	6.750	
7.625	29.70	S-95	7150	8180		8180	8180		668	841	811	0.375	6.875	6.750	
7.625	29.70	T-95	5140	8180		8180	8180		659	813	811	0.375	6.875	6.750	
7.625	29.70	H2S-95	7150	8180		8180	8180		659	813	811	0.375	6.875	6.750	
7.625	29.70	C-95	5140	8180		8180	8180		659	813	811	0.375	6.875	6.750	
7.625	29.70	HCP-110	7150	9470		9470	9470		769	960	940	0.375	6.875	6.750	
7.625	29.70	P-110	5350	9470		9470	9470		769	960	940	0.375	6.875	6.750	
7.625	33.70	L-80	6560	7900		7900	7900		664	820	778	0.430	6.765	6.640	
7.625	33.70	HCL-80	8800	7900		7900	7900		762	894	778	0.430	6.765	6.640	
7.625	33.70	N-80	6560	7900		7900	7900		674	852	778	0.430	6.765	6.640	
7.625	33.70	HCN-80	8800	7900		7900	7900		762	894	778	0.430	6.765	6.640	
7.625	33.70	C-90	7050	8880		8880	8880		733	880	875	0.430	6.765	6.640	
7.625	33.70	H2S-90	8800	8880		8880	8880		762	894	875	0.430	6.765	6.640	
7.625	33.70	S-95	8800	9380		9380	9380		783	957	923	0.430	6.765	6.640	
7.625	33.70	T-95	7280	9380		9380	9380		772	925	923	0.430	6.765	6.640	
7.625	33.70	H2S-95	8800	9380		9380	9380		772	925	923	0.430	6.765	6.640	
7.625	33.70	C-95	7280	9380		9380	9380		772	925	923	0.430	6.765	6.640	
7.625	33.70	HCP-110	8800	10860		10860	10860		901	1093	1069	0.430	6.765	6.640	
7.625	33.70	P-110	7870	10860		10860	10860		901	1093	1069	0.430	6.765	6.640	
7.625	33.70	HCQ-125	8800	12340		12340	12340		1009	1197	1215	0.430	6.765	6.640	
7.625	33.70	Q-125	8350	12340		12340	12340		1009	1197	1215	0.430	6.765	6.640	
7.625	33.70	V-150	8850	14800		14800	14800		1207	1424	1458	0.430	6.765	6.640	

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
7.625	39.00	L-80	8820	9180		9180	9180		786	945	895	0.500	6.625	6.500	
7.625	39.00	HCL-80	10600	9180		9180	9180		901	1029	895	0.500	6.625	6.500	
7.625	39.00	N-80	8820	9180		9180	9180		798	981	895	0.500	6.625	6.500	
7.625	39.00	HCN-80	10600	9180		9180	9180		901	1029	895	0.500	6.625	6.500	
7.625	39.00	C-90	9620	10330		10330	10330		867	1013	1007	0.500	6.625	6.500	
7.625	39.00	H2S-90	10600	10330		10330	10330		901	1029	1007	0.500	6.625	6.500	
7.625	39.00	S-95	10600	10900		10900	10900		926	1101	1063	0.500	6.625	6.500	
7.625	39.00	T-95	10000	10900		10900	10900		914	1065	1063	0.500	6.625	6.500	
7.625	39.00	H2S-95	10600	10900		10900	10900		914	1065	1063	0.500	6.625	6.500	
7.625	39.00	C-95	10000	10900		10900	10900		914	1065	1063	0.500	6.625	6.500	
7.625	39.00	P-110	11080	12620		12620	12620		1066	1258	1231	0.500	6.625	6.500	
7.625	39.00	Q-125	12060	14340		14340	14340		1194	1379	1399	0.500	6.625	6.500	
7.625	39.00	V-150	13440	17210		17210	17210		1428	1640	1679	0.500	6.625	6.500	
7.625	42.80	L-80	10810	10320		10320	9790		891	1053	998	0.562	6.501	6.376	
7.625	42.80	N-80	10810	10320		10320	9790		905	1093	998	0.562	6.501	6.376	
7.625	42.80	C-90	11890	11610		11610	11010		983	1129	1122	0.562	6.501	6.376	
7.625	42.80	T-95	12410	12250		12250	11620		1037	1187	1185	0.562	6.501	6.376	
7.625	42.80	C-95	12410	12250		12250	11620		1037	1187	1185	0.562	6.501	6.376	
7.625	42.80	P-110	13920	14190		14190	13460		1210	1402	1372	0.562	6.501	6.376	
7.625	42.80	Q-125	15350	16120		16120	15290		1355	1536	1559	0.562	6.501	6.376	
7.625	45.30	L-80	11510	10920		10490	9790		947	1109	1051	0.595	6.435	6.310	
7.625	45.30	HCL-80	12900	10920		10490	9790		1086	1177	1051	0.595	6.435	6.310	
7.625	45.30	N-80	11510	10920		10490	9790		962	1152	1051	0.595	6.435	6.310	
7.625	45.30	HCN-80	12900	10920		10490	9790		1086	1208	1051	0.595	6.435	6.310	
7.625	45.30	C-90	12950	12290		11810	11010		1045	1189	1183	0.595	6.435	6.310	
7.625	45.30	H2S-90	12950	12290		11810	11010		1086	1208	1183	0.595	6.435	6.310	
7.625	45.30	S-95	13660	12970		12460	11620		1116	1293	1248	0.595	6.435	6.310	
7.625	45.30	T-95	13660	12970		12460	11620		1101	1251	1248	0.595	6.435	6.310	
7.625	45.30	H2S-95	13660	12970		12460	11620		1101	1251	1248	0.595	6.435	6.310	
7.625	45.30	C-95	13660	12970		12460	11620		1101	1251	1248	0.595	6.435	6.310	
7.625	45.30	P-110	15430	15020		14430	13460		1285	1477	1446	0.595	6.435	6.310	
7.625	45.30	Q-125	17090	17070		16400	15290		1439	1619	1643	0.595	6.435	6.310	
7.625	45.30	V-150	19660	20480		19680	18350		1721	1926	1971	0.595	6.435	6.310	
7.625	47.10	L-80	12040	11480		10490	9790		997	1160	1100	0.625	6.375	6.250	
7.625	47.10	N-80	12040	11480		10490	9790		1013	1205	1100	0.625	6.375	6.250	
7.625	47.10	C-90	13540	12910		11810	11010		1100	1238	1237	0.625	6.375	6.250	
7.625	47.10	T-95	14300	13630		12460	11620		1159	1300	1306	0.625	6.375	6.250	
7.625	47.10	C-95	14300	13630		12460	11620		1159	1300	1306	0.625	6.375	6.250	
7.625	47.10	P-110	16550	15780		14430	13460		1353	1545	1512	0.625	6.375	6.250	
7.625	47.10	Q-125	18700	17930		16400	15290		1515	1672	1718	0.625	6.375	6.250	
7.625	51.20	C-90	14760	14190							1348	0.687	6.251	6.126	
7.625	51.20	T-95	15580	14980							1423	0.687	6.251	6.126	
7.625	55.30	C-90	15960	15490							1458	0.750	6.125	6.000	
7.625	55.30	T-95	16850	16350							1539	0.750	6.125	6.000	