

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
9.625	32.30	H-40	1370	2270	2270			254			365	0.312	9.001	8.845	
9.625	36.00	H-40	1720	2560	2560			294			410	0.352	8.921	8.765	
9.625	36.00	J-55	2020	3520	3520	3520	3520	394	453	639	564	0.352	8.921	8.765	
9.625	36.00	K-55	2020	3520	3520	3520	3520	423	489	755	564	0.352	8.921	8.765	
9.625	36.00	HCK-55	2980	3520	3520	3520	3520	526	605	829	564	0.352	8.921	8.765	
9.625	40.00	J-55	2570	3950	3950	3950	3950	452	520	714	630	0.395	8.835	8.679	8.750
9.625	40.00	K-55	2570	3950	3950	3950	3950	486	561	843	630	0.395	8.835	8.679	8.750
9.625	40.00	HCK-55	4230	3950	3950	3950	3950	604	64	926	630	0.395	8.835	8.679	8.750
9.625	40.00	L-80	3090	5750		5750	5750		727	947	916	0.395	8.835	8.679	8.750
9.625	40.00	HCL-80	4230	5750		5750	5750		837	1042	916	0.395	8.835	8.679	8.750
9.625	40.00	N-80	3090	5750		5750	5750		737	979	916	0.395	8.835	8.679	8.750
9.625	40.00	HCN-80	4230	5750		5750	5750		837	1042	916	0.395	8.835	8.679	8.750
9.625	40.00	C-90	3250	6460		6460	6460		804	1021	1031	0.395	8.835	8.679	8.750
9.625	40.00	H2S-90	4230	6460		6460	6460		837	1042	1031	0.395	8.835	8.679	8.750
9.625	40.00	S-95	4230	6820		6820	6820		858	1106	1088	0.395	8.835	8.679	8.750
9.625	40.00	T-95	3320	6820		6820	6820		847	1074	1088	0.395	8.835	8.679	8.750
9.625	40.00	H2S-95	4230	6820		6820	6820		847	1074	1088	0.395	8.835	8.679	8.750
9.625	40.00	C-95	3320	6820		6820	6820		847	1074	1088	0.395	8.835	8.679	8.750
9.625	43.50	L-80	3810	6330		6330	6330		813	1038	1005	0.435	8.755	8.599	8.625
9.625	43.50	HCL-80	5600	6330		6330	6330		936	1142	1005	0.435	8.755	8.599	8.625
9.625	43.50	N-80	3810	6330		6330	6330		825	1074	1005	0.435	8.755	8.599	8.625
9.625	43.50	HCN-80	5600	6330		6330	6330		936	1142	1005	0.435	8.755	8.599	8.625
9.625	43.50	C-90	4010	7120		7120	7120		899	1119	1130	0.435	8.755	8.599	
9.625	43.50	H2S-90	5600	7120		7120	7120		936	1142	1130	0.435	8.755	8.599	8.625
9.625	43.50	S-95	5600	7510		7510	7510		959	1213	1193	0.435	8.755	8.599	8.625
9.625	43.50	T-95	4120	7510		7510	7510		948	1178	1193	0.435	8.755	8.599	
9.625	43.50	H2S-95	5600	7510		7510	7510		948	1178	1193	0.435	8.755	8.599	8.625
9.625	43.50	C-95	4120	7510		7510	7510		948	1178	1193	0.435	8.755	8.599	8.625
9.625	43.50	HCP-110	5600	8700		8700	8700		1106	1388	1381	0.435	8.755	8.599	8.625
9.625	43.50	P-110	4420	8700		8700	8700		1106	1388	1381	0.435	8.755	8.599	8.625
9.625	43.50	HCQ-125	5600	9890		9890	9890		1240	1527	1570	0.435	8.755	8.599	8.625
9.625	43.50	Q-125	4620	9890		9890	9890		1240	1527	1570	0.435	8.755	8.599	8.625
9.625	47.00	L-80	4760	6870		6870	6870		893	1122	1086	0.472	8.681	8.525	8.625
9.625	47.00	HCL-80	7100	6870		6870	6870		1027	1234	1086	0.472	8.681	8.525	8.625
9.625	47.00	N-80	4760	6870		6870	6870		905	1161	1086	0.472	8.681	8.525	8.625
9.625	47.00	HCN-80	7100	6870		6870	6870		1027	1234	1086	0.472	8.681	8.525	8.625
9.625	47.00	C-90	5000	7720		7720	7720		987	1210	1221	0.472	8.681	8.525	
9.625	47.00	H2S-90	7100	7720		7720	7720		1027	1234	1221	0.472	8.681	8.525	8.625
9.625	47.00	S-95	7100	8150		8150	8150		1053	1311	1289	0.472	8.681	8.525	8.625
9.625	47.00	T-95	5090	8150		8150	8150		1040	1273	1289	0.472	8.681	8.525	
9.625	47.00	H2S-95	7100	8150		8150	8150		1040	1273	1289	0.472	8.681	8.525	8.625
9.625	47.00	C-95	5090	8150		8150	8150		1040	1273	1289	0.472	8.681	8.525	8.625

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
9.625	47.00	HCP-110	7100	9440		9440	9440		1213	1500	1493	0.472	8.681	8.525	8.625
9.625	47.00	P-110	5300	9440		9440	9440		1213	1500	1493	0.472	8.681	8.525	8.625
9.625	47.00	HCQ-125	7100	10730		10730	10730		1361	1650	1697	0.472	8.681	8.525	8.625
9.625	47.00	Q-125	5640	10730		10730	10730		1361	1650	1697	0.472	8.681	8.525	8.625
9.625	53.50	L-80	6620	7930		7930	7930		1047	1286	1244	0.545	8.535	8.379	8.500
9.625	53.50	HCL-80	8850	7930		7930	7930		1205	1414	1244	0.545	8.535	8.379	8.500
9.625	53.50	N-80	6620	7930		7930	7930		1062	1329	1244	0.545	8.535	8.379	8.500
9.625	53.50	HCN-80	8850	7930		7930	7930		1205	1414	1244	0.545	8.535	8.379	8.500
9.625	53.50	C-90	7120	8920		8920	8920		1157	1386	1399	0.545	8.535	8.379	8.500
9.625	53.50	H2S-90	8850	8920		8920	8920		1205	1414	1399	0.545	8.535	8.379	8.500
9.625	53.50	S-95	8850	9410		9410	9410		1235	1502	1477	0.545	8.535	8.379	8.500
9.625	53.50	T-95	7340	9410		9410	9410		1220	1458	1477	0.545	8.535	8.379	8.500
9.625	53.50	H2S-95	8850	9410		9410	9410		1220	1458	1477	0.545	8.535	8.379	8.500
9.625	53.50	C-95	7340	9410		9410	9410		1220	1458	1477	0.545	8.535	8.379	8.500
9.625	53.50	HCP-110	8850	10900		10900	10900		1422	1718	1710	0.545	8.535	8.379	8.500
9.625	53.50	P-110	7950	10900		10900	10900		1422	1718	1710	0.545	8.535	8.379	8.500
9.625	53.50	HCQ-125	8850	12390		12390	12390		1595	1890	1943	0.545	8.535	8.379	8.500
9.625	53.50	Q-125	8440	12390		12390	12390		1595	1890	1943	0.545	8.535	8.379	8.500
9.625	53.50	V-150	8960	14860		14860	14860		1909	2251	2332	0.545	8.535	8.379	8.500
9.625	58.40	L-80	7890	8650		8650	8650		1151	1396	1350	0.595	8.435	8.279	8.375
9.625	58.40	N-80	7890	8650		8650	8650		1167	1443	1350	0.595	8.435	8.279	8.375
9.625	58.40	C-90	8560	9740		9740	9740		1272	1504	1519	0.595	8.435	8.279	8.375
9.625	58.40	T-95	8880	10280		10280	10280		1341	1583	1604	0.595	8.435	8.279	8.375
9.625	58.40	C-95	8880	10280		10280	10280		1341	1583	1604	0.595	8.435	8.279	8.375
9.625	58.40	P-110	9760	11900		11900	11900		1564	1865	1857	0.595	8.435	8.279	8.375
9.625	58.40	Q-125	10530	13520		13520	13520		1754	2052	2110	0.595	8.435	8.279	8.375
9.625	59.40	C-90	8980	9970							1553	0.609	8.407	8.251	
9.625	59.40	T-95	9320	10520							1634	0.609	8.407	8.251	
9.625	64.90	C-90	10800	11000							1701	0.672	8.281	8.125	
9.625	64.90	T-95	11260	11610							1796	0.672	8.281	8.125	
9.625	70.30	C-90	12610	12010							1845	0.734	8.157	8.001	
9.625	70.30	T-95	13180	12680							1948	0.734	8.157	8.001	
9.625	75.60	C-90	13670	13040							1989	0.797	8.031	7.875	
9.625	75.60	T-95	14430	13770							2100	0.797	8.031	7.875	